

## HANDLING PRECAUTIONS

1. The repair procedure for plastic body parts must conform with the type of plastic material.
2. Plastic body parts are identified by the codes in the following chart.
3. When repairing metal body parts adjoining plastic body parts (by brazing, frame cutting, welding, painting etc.), consideration must be given to the property of the plastic.

| Code | Material name                        | Heat* resistant temperature limit °C (°F) | Resistance to alcohol or gasoline  | Notes   |
|------|--------------------------------------|---|--|---|
| AAS  | Acrylonitrile<br>Acrylic Styrene     | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| ABS  | Acrylonitrile<br>Butadiene Styrene   | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| AES  | Acrylonitrile<br>Ethylene Styrene    | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| ASA  | Acrylonitrile<br>Styrene<br>Acrylate | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| CAB  | Cellulose<br>Acetate                 | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| EPDM | Ethylene<br>Propylene                | 100<br>(212)                              | Alcohol is harmless.<br>Gasoline is harmless if applied only for short time in small amounts.              | Most solvents are harmless but avoid dipping in gasoline, solvents, etc.              |
| FRP  | Fiber<br>Reinforced<br>Plastics      | 180<br>(356)                              | Alcohol and gasoline are harmless.   | Avoid alkali.   |
| EVA  | Ethylene<br>Acetate                  | 70<br>(158)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid gasoline and organic or aromatic solvents.                                      |
| PA   | Polyamide<br>(Nylon)                 | 80<br>(176)                               | Alcohol and gasoline are harmless.   | Avoid battery acid.   |
| PBT  | Polybutylene<br>Terephthalate        | 160<br>(320)                              | Alcohol and gasoline are harmless.   | Most solvents are harmless.   |
| PC   | Polycarbonate                        | 120<br>(248)                              | Alcohol is harmless.   | Avoid gasoline, brake fluid, wax, wax removers and organic solvents.<br>Avoid alkali. |

\*Temperatures higher than those listed here may result in material deformation during repair.

| Code | Material name                 | Heat* resistant temperature limit °C (°F) | Resistance to alcohol or gasoline  | Notes  |
|------|-------------------------------|---|--|--|
| PE   | Polyethylene                  | 80<br>(176)                               | Alcohol and gasoline are harmless.   | Most solvents are harmless.  |
| PET  | Polyethylene Terephthalate    | 75<br>(167)                               | Alcohol and gasoline are harmless.   | Avoid dipping in water.  |
| PMMA | Polymethyl Methacrylate       | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts.   | Avoid dipping or immersing in alcohol, gasoline, solvents, etc.          |
| POM  | Polyoxymethylene (Polyacetal) | 100<br>(212)                              | Alcohol and gasoline are harmless.   | Most solvents are harmless.  |
| PP   | Polypropylene                 | 80<br>(176)                               | Alcohol and gasoline are harmless.   | Most solvents are harmless.  |
| PPO  | Modified Polyphenylene Oxide  | 100<br>(212)                              | Alcohol is harmless.   | Gasoline is harmless if applied only for quick wiping to remove grease.  |
| PS   | Polystyrene                   | 60<br>(140)                               | Alcohol and gasoline are harmless if applied only for short time in small amounts.                                       | Avoid dipping or immersing in alcohol, gasoline, solvents, etc.          |
| PUR  | Polyurethane                  | 80<br>(176)                               | Alcohol is harmless if applied only for very short time in small amounts (e.g., quick wiping to remove grease).          | Avoid dipping or immersing in alcohol, gasoline, solvents, etc.          |
| PVC  | Polyvinylchloride (Vinyl)     | 80<br>(176)                               | Alcohol and gasoline are harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease). | Avoid dipping or immersing in alcohol, gasoline, solvents, etc.          |
| SAN  | Styrene Acrylonitrile         | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease).               | Avoid dipping or immersing in alcohol, gasoline, solvents etc.           |
| TPO  | Thermoplastic Olefine         | 80<br>(176)                               | Alcohol is harmless.<br>Gasoline is harmless if applied only for short time in small amounts.                            | Most solvents are harmless but avoid dipping in gasoline, solvents, etc. |
| TPU  | Thermoplastic Polyurethane    | 80<br>(176)                               | Alcohol is harmless if applied only for short time in small amounts (e.g., quick wiping to remove grease).               | Avoid dipping or immersing in alcohol, gasoline, solvents, etc.          |
| TSOP | TOYOTA Super Olefine Polymer  | 80<br>(176)                               | Alcohol and gasoline are harmless.   | Most solvents are harmless.  |
| UP   | Unsaturated Polyester         | 110<br>(233)                              | Alcohol and gasoline are harmless.   | Avoid alkali.  |

\*Temperatures higher than those listed here may result in material deformation during repair.